

Test report no.: <i>Testrapport nr.:</i>	89224955 001	Order No.: <i>Opdracht nr.:</i>	224955	Page 1 of 5 <i>Pagina 1 van 5</i>
Client Reference No.: <i>Klantreferentie nr.:</i>	Fiberdeck Harmony test	Order date: <i>Opdrachtdatum:</i>	2024-10-08	
Client: <i>Klant:</i>	Felix Clercx Handelsonderneming B.V., Maisdijk 5, 5704 RM Helmond, The Netherlands			
Test item: <i>Testvoorwerp:</i>	Floor covering			
Identification/ Type No.: <i>Benaming / Type nr.:</i>	Fiberdeck Harmony			
Order content: <i>Inhoud opdracht:</i>	The determination of selected parameter.			
Test specification: <i>Testomschrijving:</i>	EN 16165:2021 - Annex B - Shod ramp test The determination of slip resistance of pedestrian surfaces.			
Date of sample receipt: <i>Ontvangstdatum monster:</i>	2024-10-04			
Test sample No: <i>Testproefstuk nr.:</i>	MT24-224955.01 and MT24-224955.02			
Testing period: <i>Testperiode:</i>	2024-10-04 - 2024-10-22			
Place of testing: <i>Testlocatie:</i>	Westervoortsedijk 73, 6827 AV Arnhem			
Testing laboratory: <i>Testlaboratorium:</i>	TÜV Rheinland Nederland B.V.			
Test result*: <i>Testresultaat*:</i>	See individual test results			
tested by: <i>getest door:</i>		authorized by: <i>geautoriseerd door:</i>		
Date: 2024-10-23 <i>Datum:</i>	Signed by: Michiel van de Vlekkert	Issue Date: 2024-10-23 <i>Datum uitgave:</i>	Ondertekend door: Klaas Kooistra	
Position / functie:	Engineer	Position / functie:	Expert	
Others / <i>Andere:</i>				
Condition of the test item at delivery: <i>Toestand van het test voorwerp bij ontvangst:</i>	Test item complete and undamaged			
* Legend:	P(ass) = passed a.m. test specification(s)	F(ail) = failed a.m. test specification(s)	N/A = not applicable	N/T = not tested
* Legenda:	P(ass) = voldoet aan test omschrijving	F(ail) = voldoet niet aan test omschrijving	N/A = niet van toepassing	N/T = niet getest
This test report only relates to the a. m. test sample. Without permission of the test center this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any test mark. <i>Dit testrapport heeft alleen betrekking op het voornoemde test voorwerp. Zonder toestemming van het testcentrum mag dit testrapport niet in delen worden vermenigvuldigd. Dit keuringsrapport geeft geen recht op het dragen van enig keurmerk.</i>				

Test report no.: 89224955 001
Testrapport nr.:

Page 2 of 5
Pagina 2 van 5

Remarks
Opmerkingen

- 1** The equipment used during the specified testing period was calibrated according to our test laboratory calibration program. The equipment fulfils the requirements included in the relevant standards. The traceability of the test equipment used is ensured by compliance with the regulations of our management system. The decision rule for statements of conformity in this test report is based on the "Zero Guard Band Rule" and "Simple Acceptance" in accordance to and ILAC-G8:09/2019 and IEC Guide 115:2021, unless otherwise specified in the applied standard mentioned on Page 1 of this report or requested by the customer. This means that measurement uncertainty is not taken in account.

De apparatuur die tijdens de gespecificeerde testperiode is gebruikt, is gekalibreerd volgens ons testlaboratoriumkalibratieprogramma. De apparatuur voldoet aan de eisen die zijn opgenomen in de relevante normen. De traceerbaarheid van de gebruikte testapparatuur wordt gewaarborgd door naleving van de voorschriften van ons managementsysteem. De beslisregel voor conformiteitsverklaringen in dit testrapport is gebaseerd op de "Zero Guard Band Rule" en "Simple Acceptance" in overeenstemming met en ILAC - G8:09/2019 en IEC Guide 115:2021, tenzij anders aangegeven in de toegepaste norm vermeld op pagina 1 van dit rapport of aangevraagd door de klant. Dit betekent dat er geen rekening wordt gehouden met de meetonzekerheid.
- 2** As contractually agreed, this document has been signed digitally only. TÜV Rheinland has not verified and is unable to verify which legal or other pertaining requirements are applicable for this document. Such verification is within the responsibility of the user of this document. Upon request by its client, TÜV Rheinland can confirm the validity of the digital signature by a separate document. Such request shall be addressed to our Sales department. An environmental fee for such additional service will be charged.

Zoals contractueel overeengekomen is dit document enkel digitaal ondertekend. TÜV Rheinland heeft niet geverifieerd en kan niet verifiëren welke wettelijke of andere vereisten van toepassing zijn op dit document. Een dergelijke verificatie valt onder de verantwoordelijkheid van de gebruiker van het document. Op verzoek van de opdrachtgever kan TÜV Rheinland de geldigheid van de digitale handtekening bevestigen door een apart document. Een dergelijk verzoek moet worden gericht aan onze verkoopafdeling. Voor een dergelijke extra service zal een milieutoeslag in rekening worden gebracht.
- 3** Test clauses with remark of * are subcontracted to qualified subcontractors and described under the respective test clause in the report. Tests clauses marked with ^a are performed under EN ISO/IEC 17025 accreditation. Deviations of testing specification(s), test locations or customer requirements are listed in specific test clause in the report. No opinions or interpretation are included in this report. This test report consists of multiple pages and is only to be read as a whole. The number of pages can be seen in the header on the top right of each page, the report ends when the last page is reached. TÜV Rheinland Nederland B.V. is solely responsible for the content.

*Test onderdelen welke met * zijn gemarkeerd zijn uitbesteed aan gekwalificeerde onderaannemers en zijn beschreven in het respectievelijke test onderdeel van dit rapport. Test onderdelen welke met ^a zijn gemarkeerd zijn onder EN ISO/IEC 17025 accreditatie uitgevoerd. Afwijkingen van testspecificatie(s), testlocaties of klant eisen zijn vermeld in het van toepassing zijnde onderdeel in het rapport. Er zijn geen opinies en interpretaties opgenomen binnen het rapport. Dit rapport bestaat uit meerdere pagina's en dient als geheel gelezen te worden. Het aantal pagina's is rechtsboven in de koptekst van dit rapport vermeld en eindigt wanneer de laatste pagina is bereikt. TÜV Rheinland Nederland is als enige verantwoordelijk voor de inhoud van het rapport.*
- 4** All rights reserved. No part of this report may be reproduced, provided to and/or examined by third parties, and/or published by print, photoprint, microfilm, in electronic form or any other means without the explicit previous written consent of TÜV Rheinland Nederland B.V.

In case this report was drafted within the context of an assignment to TÜV Rheinland Nederland B.V., the rights and obligations of contracting parties are subject to the General Terms & Conditions for Advisory, Research and Certification assignments to TÜV Rheinland Nederland B.V. and/or the relevant agreement concluded between the contracting parties. © 2010 TÜV Rheinland Nederland.

Alle rechten voorbehouden. Niets uit dit rapport mag worden veelevoudigd, aan derden ter beschikking gesteld en/of door derden onderzocht en/of openbaar gemaakt door middel van druk, fotokopie, microfilm, in elektronische vorm of op welke andere wijze dan ook, zonder uitdrukkelijke voorafgaande schriftelijke toestemming van TÜV Rheinland Nederland B.V.

Indien dit rapport is opgesteld in het kader van een opdracht aan TÜV Rheinland Nederland B.V., zijn de rechten en verplichtingen van contractpartijen onderworpen aan de Algemene Voorwaarden voor Advies-, Onderzoeks- en Certificeringsopdrachten aan TÜV Rheinland Nederland B.V. en/of de betreffende overeenkomst tussen de contractpartijen. © 2010 TÜV Rheinland Nederland

Test report no.: 89224955 001
Testrapport nr.:

Page 3 of 5
Pagina 3 van 5

Clause Deel	Requirements - Tests / Vereisten - Tests	Measuring results – Remarks Meetresultaten – Opmerkingen	Result Resultaat
----------------	---	---	---------------------

1	Product details: <i>Product details:</i>	Product name: Fiberdeck Harmony	
2	Other: <i>Andere:</i>	Test sample(s), as well sample information, description, product details and intended usage was provided by customer.	
3	Test sample obtaining: <i>Selectie van het proefstuk:</i>	☒ Sending by customer ☐ Sampling by TÜV Rheinland Group ☐ Others:	

Figure 1: Picture of the received sample (length surface)



Figure 2: Picture of the received sample (length back)



Figure 3: Picture of the received sample (width surface)




Figure 4: Picture of the received sample (width back)



Test report no.: 89224955 001
Testrapport nr.:

Page 4 of 5
Pagina 4 van 5

Clause Deel	Requirements - Tests / Vereisten - Tests	Measuring results – Remarks Meetresultaten – Opmerkingen	Result Resultaat
1	Determination of slip resistance of pedestrian surfaces. EN 16165:2021 – Annex B – Shod ramp test		
	Testing environment	20 ± 5 °C	
	Date of test	2024-10-22	
	Surface structure	structured	
	Test direction	length	
	Sample number	MT24-224955.01	
	Test result(s)		
	Ramp test value, α_{shod}	24 °	P ☐ F ☐ N/A ☒ N/T ☐
	Evaluation of test result against former DIN 51130:2014	Class R11*	
	Corrected mean angle of acceptance, α_{ges}		
6 ° - 10 ° R9			
> 10 ° - 19 ° R10			
> 19 ° - 27 ° R11			
> 27 ° - 35 ° R12			
> 35 ° R13			
*DIN 51130:2014 is replaced by EN 16165:2021. Because no classification criteria are mentioned in the EN 16165:2021, the classification mentioned should be considered as indicative and used for comparison reasons only.			

Test report no.: 89224955 001
Testrapport nr.:

Page 5 of 5
Pagina 5 van 5

Clause Deel	Requirements - Tests / Vereisten - Tests	Measuring results – Remarks Meetresultaten – Opmerkingen	Result Resultaat
2	Determination of slip resistance of pedestrian surfaces. EN 16165:2021 – Annex B – Shod ramp test		
	Testing environment	20 ± 5 °C	
	Date of test	2024-10-22	
	Surface structure	structured	
	Test direction	width	
	Sample number	MT24-224955.02	
	Test result(s)		
	Ramp test value, α_{shod}	28 °	P ☐ F ☐ N/A ☒ N/T ☐
	Evaluation of test result against former DIN 51130:2014	Class R12*	
	Corrected mean angle of acceptance, α_{ges}		
Class of slip resistance			
6 ° - 10 ° R9			
> 10 ° - 19 ° R10			
> 19 ° - 27 ° R11			
> 27 ° - 35 ° R12			
> 35 ° R13			
*DIN 51130:2014 is replaced by EN 16165:2021. Because no classification criteria are mentioned in the EN 16165:2021, the classification mentioned should be considered as indicative and used for comparison reasons only.			